

Large Speedy 2000 Moisture Meter

Speedy Moisture Tester for roads, aggregates, sand and concrete.



The New Speedy 2000 series of moisture testers combines time proven dependability of the calcium carbide pressure test procedure with the convenience of an electronic balance.

Knowledge of the moisture content of soils and construction materials is of great importance to engineers involved with the construction of roads, bridges and other civil structures. Throughout the world, the Large Speedy moisture tester is used on construction sites to establish the percent moisture content (%MC) of these materials before the actual construction work commences.

The Speedy moisture tester is a portable-sampling instrument used to determine the moisture content of a broad range of materials. It comprises a hand held vessel incorporating a pressure gauge and a precision balance, mounted in an integral carry case.

Features include:

- requires no power source
- does not need to be calibrated for different soils
- each test takes just a few minutes
- safe to use
- no requirement for a user licence
- portable, robust and accurate
- endorsed by many international official bodies

Moisture measurements are obtained by following a simple test procedure:

- Prepare and weigh the material sample using the electronic balance.
- Place the sample in the Speedy vessel.
- Add the reagent to the recess in the Speedy cap and seal the vessel.
- Shake the Speedy to mix the reagent with the sample.
- Read the moisture content directly from the integral gauge.



Roads and Highways

Knowledge of the moisture content of soil is crucial throughout geotechnical engineering practice. Engineers use the Speedy for field control of compacted earth embankments and other structures and to measure the water content of soil to ensure it is within specified ranges. The Speedy moisture tester is ideal for this, being accurate, robust and simple to use.

Aggregates, Sand and Concrete

The Moisture content of freshly mixed concrete affects the workability, blending, segregation, strength and drying rate of the finished product. The Speedy tester is an ideal on-site quality control tool. Moisture levels of aggregates and sand can be checked prior to use to ensure that the correct amount of water is added when mixing with cement. The moisture content of ready-mix cement concrete can also be checked, to ensure it is in specification.

Technical Specifications

Large Speedy vessel fitted with calibrated pressure gauge, electronic balance, heavy duty carry case with fitted foam inserts, cleaning brush and cloth, two steel sample-pulverising balls, measuring scoop, instructions.

| | |
|---|--------------------|
| Nominal gross weight: | 6kg |
| Nominal gross dimensions: | 51 x 38 x 20 cm |
| Moisture measurement range expressed as a percentage of the wet weight of the sample: | 0 - 20% |
| | 0 - 10% |
| | 0 - 50% |
| Sample weight: | 0 - 20% range: 20g |
| | 0 - 10% range: 40g |
| | 0 - 50% range: 8g |

Maximum sample size: 20mm

NB: Please note that the calcium carbide reagent that is used with the Speedy testers must be ordered separately.



BAMR (Pty) Ltd, PO Box 23973, Claremont, 7735, South Africa
 Ph : 27 (0)21 683 2100, Fax : 27 (0)21 674 1485
 Email : sales@bamr.co.za, Web : www.bamr.co.za